

# Express Brown

## (spec sheet)

	<u>1" screened</u>	<u>1/2" screened</u>	<u>1" minus</u>	<u>1/2" minus</u>	<u>1/4" minus</u>	<u>4" minus</u>
<b>Bulk Density:</b>	<b>86.2</b>	<b>89</b>	<b>108.1</b>	<b>107.8</b>	<b>102</b>	<b>111</b>
(lbs. / cu. Ft.)						

<u>Sieve</u>	<u>% Ret. % Pass</u>		<u>%Ret. % Pass</u>		<u>%Ret. % Pass</u>		<u>%Ret. % Pass</u>		<u>%Ret. % Pass</u>		<u>%Ret. % Pass</u>	
<b>4"</b>	0	100	0	100	0	100	0	100	0	100	1	99
<b>3"</b>	0	100	0	100	0	100	0	100	0	100	11	89
<b>2"</b>	0	100	0	100	0	100	0	100	0	100	14	86
<b>1-1/2"</b>	0	100	0	100	0	100	0	100	0	100	20	80
<b>1-1/4"</b>	0	100	0	100	2	98	0	100	0	100	19	79
<b>1"</b>	17	83	0	100	10	90	0	100	0	100	21	79
<b>3/4"</b>	61	39	2	98	20	80	1	99	0	100	27	73
<b>1/2"</b>	95	5	43.5	56.5	28	72	23	77	0	100	30	70
<b>3/8"</b>	97	3	82	18	33	67	36	64	0	100	35	65
<b>1/4"</b>	98	2	98	2	42	58	48	52	2	98	41	59
<b>#4</b>	99	1	99	1	49	51	54	46	12	88	49	51
<b>#8</b>	99	1	99	1	65	35	66	34	33	67	57	43
<b>#10</b>					15	23	3	32	38	62	11	32
<b>#16</b>					21	17	9	26	48	52	14	29
<b>#30</b>	99	1	99	1	16	22	14	21	61	39	15	28
<b>#40</b>					20	18	16	18	65	35	17	26
<b>#50</b>					22	16	18	16	69	31	18.5	24.5
<b>#100</b>					21.5	16.5	21	13	76	24	21	22
<b>#200</b>	99.5	0.5	99	1	27.5	10.5	23	11	79.8	20.2	26	17

- \*\* This gradation report was taken from several samples and averaged together. This spec sheet is to be used as a reference only.
- \*\* Decorative Rock is a natural product, thus allowing for color and size variations. Granite Express cannot guarantee size or color consistency.
- \*\* Every Quarry will have different gradations for the same products based upon different geologic formations, and different crushing process.

# Express Gold

## (spec sheet)

	<u>1" screened</u>	<u>1/2" screened</u>	<u>1" minus</u>	<u>1/2" minus</u>	<u>1/4" minus</u>	<u>4" minus</u>
<b>Bulk Density:</b>	<b>85.4</b>	<b>86.3</b>	<b>106.5</b>	<b>106.2</b>	<b>102</b>	<b>110.8</b>
(lbs. / cu. Ft.)						

Sieve	% Ret.	% Pass	%Ret.	% Pass	%Ret.	% Pass	%Ret.	% Pass	%Ret.	% Pass	%Ret.	% Pass
4"	0	100	0	100	0	100	0	100	0	100	1	99
3"	0	100	0	100	0	100	0	100	0	100	11	89
2"	0	100	0	100	0	100	0	100	0	100	14	86
1-1/2"	0	100	0	100	0	100	0	100	0	100	20	80
1-1/4"	0	100	0	100	2	98	0	100	0	100	17	83
1"	13	87	0	100	7	93	0	100	0	100	21	79
3/4"	65	35	2	98	11	89	1	99	0	100	27	73
1/2"	83	17	43	57	30	70	18	82	0	100	30	70
3/8"	97	3	82	18	33	67	36	64	0	100	38	62
1/4"	98	2	98	2	42	58	45	55	1	99	41	59
#4	99	1	98	2	50	50	49	51	12	88	49	51
#8	99	1	98	2	62	38	65.5	34.5	33	67	57	43
#10					16	22	3	32	38	62	11	32
#16					20.5	17.5	9	26	50	50	14	29
#30	99	1	99	1	16	22	14	21	61	39	15	28
#40					20	18	16	18	65	35	17	26
#50					21	17	18	16	69	31	18.5	24.5
#100					22	16	21	13	76	24	21	22
#200	99	1	99	1	28	10	23	12	80	20	25	18

\*\* This gradation report was taken from several samples and averaged together. This spec sheet is to be used as a reference only.

\*\* Decorative Rock is a natural product, thus allowing for color and size variations. Granite Express cannot guarantee size or color consistency.

\*\* Every Quarry will have different gradations for the same products based upon different geologic formations, and different crushing process.

# **EXPRESS ROSE**

## **(spec sheet)**

	<u><b>1" screened</b></u>	<u><b>1/2" screened</b></u>	<u><b>1" minus</b></u>	<u><b>1/2" minus</b></u>	<u><b>1/4" minus</b></u>	<u><b>4" minus</b></u>
<b>Bulk Density:</b> (lbs. / cu. Ft.)	<b>85.9</b>	<b>88.9</b>	<b>107.9</b>	<b>107.5</b>	<b>101.8</b>	<b>111.8</b>
<u><b>Sieve</b></u>	<u><b>% Ret. % Pass</b></u>	<u><b>%Ret. % Pass</b></u>	<u><b>%Ret. % Pass</b></u>	<u><b>%Ret. % Pass</b></u>	<u><b>%Ret. % Pass</b></u>	<u><b>%Ret. % Pass</b></u>
<b>4"</b>	0 100	0 100	0 100	0 100	0 100	4.5 95.5
<b>3"</b>	0 100	0 100	0 100	0 100	0 100	11 89
<b>2"</b>	0 100	0 100	0 100	0 100	0 100	14 86
<b>1-1/2"</b>	0 100	0 100	0 100	0 100	0 100	18 82
<b>1-1/4"</b>	0 100	0 100	2 98	0 100	0 100	17 83
<b>1"</b>	13 87	0 100	7 93	0 100	0 100	21 79
<b>3/4"</b>	65 35	2 98	11 89	1 99	0 100	27 73
<b>1/2"</b>	95 5	43 57	28 72	18 82	0 100	30 70
<b>3/8"</b>	97 3	82 18	33 67	36 64	0 100	35 65
<b>1/4"</b>	99 1	98 2	42 58	48 52	1 99	41 59
<b>#4</b>	99 1	98 2	50 50	49 51	12 88	49 51
<b>#8</b>	99 1	98 2	62 38	63.3 36.7	33 67	57 43
<b>#10</b>			15.2 22.8	3 32	38 62	11 32
<b>#16</b>			20.5 17.5	9 26	50 50	14 29
<b>#30</b>	99 1	99 1	16 22	14 21	61 39	15 28
<b>#40</b>			20 18	16 18	65 35	17 26
<b>#50</b>			22 14	18 16	69 31	18.5 24.5
<b>#100</b>			21.5 16.5	21 13	76 24	21 22
<b>#200</b>	99.5 0.5	99 1	27.5 10.5	23 12	79.8 20.2	24.6 18.4

- \*\* This gradation report was taken from several samples and averaged together. This spec sheet is to be used as a reference only.
- \*\* Decorative Rock is a natural product, thus allowing for color and size variations. Granite Express cannot guarantee size or color consistency.
- \*\* Every Quarry will have different gradations for the same products based upon different geologic formations, and different crushing process.

# Tanner Gold

## (spec sheet)

	<u>1" screened</u>		<u>1/2" screened</u>		<u>1" minus</u>		<u>1/2" minus</u>		<u>1/4" minus</u>		<u>4" minus</u>	
<b>Bulk Density:</b>	85.9		88.9		107.9		107.52		101.75		111.8	
(lbs. / cu. Ft.)												
<u>Sieve</u>	<u>% Ret.</u>	<u>% Pass</u>	<u>%Ret.</u>	<u>% Pass</u>	<u>%Ret.</u>	<u>% Pass</u>	<u>%Ret.</u>	<u>% Pass</u>	<u>%Ret.</u>	<u>% Pass</u>	<u>%Ret.</u>	<u>% Pass</u>
4"	0	100	0	100	0	100	0	100	0	100	4.5	95.5
3"	0	100	0	100	0	100	0	100	0	100	11	89
2"	0	100	0	100	0	100	0	100	0	100	14	86
1-1/2"	0	100	0	100	0	100	0	100	0	100	18	82
1-1/4"	0	100	0	100	2	98	0	100	0	100	17	83
1"	13	87	0	100	7	93	0	100	0	100	21	79
3/4"	65	35	2	98	11	89	1	99	0	100	27	73
1/2"	95	5	43	57	28	72	18	82	0	100	30	70
3/8"	97	3	82	18	33	67	36	64	0	100	35	65
1/4"	99	1	98	2	42	58	48	52	1	99	41	59
#4	99	1	98	2	50	50	49	51	12	88	49	51
#8	99	1	98	2	62	38	63.3	36.7	33	67	57	43
#10					15.2	22.8	3	32	38	62	11	32
#16					20.5	17.5	9	26	50	50	14	29
#30	99	1	99	1	16	22	14	21	61	39	15	28
#40					20	18	16	18	65	35	17	26
#50					22	14	18	16	69	31	18.5	24.5
#100					21.5	16.5	21	13	76	24	21	22
#200	99.5	0.5	99	1	27.5	10.5	23	12	79.8	20.2	24.6	18.4

\*\* This gradation report was taken from several samples and averaged together. This spec sheet is to be used as a reference only.

\*\* Decorative Rock is a natural product, thus allowing for color and size variations. Granite Express cannot guarantee size or color consistency.

\*\* Every Quarry will have different gradations for the same products based upon different geologic formations, and different crushing process.